

Product Name & Description

Celgard® 3419S 25µm Monolayer Microporous Membrane (PP) & Celgard® 3420 220µm Monolayer Non-Woven Separator (PP)
Surfactant Coated Hydrophilic Membranes



Primary Applications

NiCd Battery Systems

Large Format Vented Systems in Aviation, Transportation and Telecommunication Backup

Product Benefits

- 3419S provides gas barrier for thermal stability
- 3420 acts as an ideal separator in NiCd systems
- Both 3419S & 3420 are coated with the same complex proprietary surfactant for rapid wetting
- Combination of 3419S and 3420 is designed to meet the MIL-PRF-81757D performance specification for aircraft batteries

Packaging

Please contact your Celgard representative for more information on product roll lengths and slit widths.

3419S Technical Data (Typical Properties)

Basic Film Properties	Unit of Measure	Typical Value
Coated Thickness	µm	25
Gurley (ASTM)	Seconds	40
Shrinkage @ 90°C / 1 Hour (typical)	%	2.3 / 5.0
Coat Wet Out (max – internal method)	seconds	30

3420 Technical Data (Typical Properties)

Basic Film Properties	Unit of Measure	Typical Value
Coated Thickness (max)	µm	229
Coat Wet Out (max – internal method)	seconds	5

At the Center of Membrane Innovation

Manufacturing Locations

United States

Headquarters, Manufacturing and R&D at Charlotte
 13800 South Lakes Drive
 Charlotte, North Carolina
 28273 United States
 Phone: +1 704-588-5310
 Fax: +1 704-588-5319

Manufacturing and R&D at Concord
 390 Business Boulevard
 Concord, North Carolina
 28027 United States
 Phone: +1 704-720-5200
 Fax: +1 704-720-5211

China

Manufacturing & Distribution
 Celgard (Shanghai) Materials Technology Co., Ltd.
 Building 2, 180 North Riying Road,
 China (Shanghai) Pilot Free Trade Zone,
 Pudong New District, Shanghai, 200131 China
 Phone: +86 (21) 5028 0001

Sales Offices

Europe, Middle East & Africa (EMEA)

Sales & Technical Service
 Phone: +33 3 88 82 41 08
 Fax: +33 3 55 03 59 03

Korea

Sales & Technical Service
 Phone: +82 41-905-6001
 Fax: +82 41-905-6099

China

Sales & Technical Service
 Phone: +86 21 3813 9910
 Fax: +86 21 3813 9911

Japan

Sales & Technical Service
 Phone: +81 3-6891-3750
 Fax: +81 3-6891-3769

India & South Asia

Sales & Technical Service
 Phone: +91 80 4256 1104
 Fax: +91 80 4256 1106



DISCLAIMER, LIMITED WARRANTY: This product is to be used only by persons familiar with its use. It must be maintained within the stated limitations. Most non-developmental, purchased Celgard products are sold subject to Celgard's then current Sales T&C's. No other warranty is expressed or implied. Purchaser assumes all responsibility for the use and safety of this product. To the best of our knowledge, the information contained herein is accurate. However, neither CELGARD, LLC nor any of its affiliates assumes any liability whatsoever for the accuracy or completeness of this information. Final determination of the suitability of any material and whether there is any infringement of patents is the sole responsibility of the user. Users of any substance should satisfy themselves by independent investigation that the material can be used safely. We may have described certain hazards, but we cannot guarantee that these are the only hazards that exist. An Article Information Sheet may be available upon request. This product may be provided in confidence under NDA and as such is Celgard Confidential.

